



JD-5086 Series

UV & Moisture Cure coating

UL File No. E526815

Features

- A solvent free, one-component acrylate polyurethane coating.
- Cure rapidly, fluorescent identification, convenient for visual inspection of coating appearance.
- Shadowed sections can be cured by the moisture in the air.
- High dielectric breakdown strength and insulation resistance including humid and harsh conditions.
- The cured film has good chemical resistance, and provides protection against mechanical stress, contaminants, moisture, dust and corrosive gases.
- No benzene, toluene and xylene in the solvent.
- Compliance with UL94 V-0, IPC-CC-830 and RoHS Directive.

Physical Properties

Appearance	:	Colorless transparent liquid
Viscosity	:	ISO 2555 JD-5086-80 : 55 ~ 105 cps JD-5086-250 : 175 ~ 325 cps JD-5086-500 : 350 ~ 700 cps
Density	:	@25°C, ISO 2811 1.02 ~ 1.17 g/ml
Solid Content	:	ISO 3251 100%
UV Curing time	:	1000 ~ 3000mJ/cm ² 5 ~ 30 sec
Hardness	:	@25°C, ISO 868-2003 Shore D 60
Thermal Shock	:	@-40°C~+125°C Pass
Glass Transition Temperature (Tg)	:	ISO 11357 (DSC) 56°C
Cross Cut Test	:	@25°C, GB 9286 Class 0
Salt Fog Test	:	@25°C, IPC-TM-650 Pass
Dielectric Constant	:	@25°C, ASTM D 150 2.6
Permittivity	:	@25°C, ASTM D 150 0.012
Dielectric Strength	:	@25°C, ASTM D 115 60 kV/mm
Insulation Resistance	:	@25°C, MIL-I-46058C 1.0 x 10 ¹⁵ ohm
Volume Resistivity	:	@25°C, IEC 60464 1.7 x 10 ¹⁴ ohm · cm
Shelf Life	:	@25°C, Unopened 1 Year

Handling & Storage

- For high strength bonding, clean the contact surface to remove dust, grease and all other contaminants before applying the adhesive.
- JD-5086 should be stored in the shade and a cool place. Avoid the contact with any light (including ultraviolet ray). Put the lid back on immediately after each use to prevent any possibility of light exposure, which will affect the product performances. to prevent any possibility of light exposure, which will affect the product performances.



傑地有限公司
 JASDI CHEMICALS CO., LTD.
 Website: www.jasdi.com.tw
 E-mail: jasdikao@ms21.hinet.com.tw

台北 Taipei :+886-2-26008672
 台中 Taichung :+886-4-25685848
 東莞 Dongguan :+86-769-88188707
 上海 Shanghai :+86-21-58356975

JV2404-541